

Regular application (pressure grade 4~7kgf/cm², safety factor 2.5)

Size		Outer diameter	Thickness	Pressure	Length	Weight
mm	Inch	mm	mm	kgf/cm ²	M	kg/M
40	1 1/2	48.0±0.50	3.0±0.25	8	5/50	0.405
50	2	60.0±0.60	3.5±0.30	7	5/50	0.593
65	2 1/2	76.0±1.10	4.0±0.35	6	5	0.869
75	3	89.0±1.30	5.0±0.40	6	5	1.260
100	4	114.0±1.45	5.5±0.45	5	5	1.790
125	5	140.0±1.80	6.5±0.55	5	5	2.603
150	6	165.0±2.00	7.0±0.60	5	5	3.318
200	8	216.0±2.30	8.0±0.65	4	5	4.992
250	10	267.0±2.70	9.0±0.75	4	5	6.966
300	12	318.0±3.20	10.0±0.80	4	5	9.240
350	14	370.0±3.30	14.2±1.00	4	5	15.157
400	16	420.0±3.70	16.2±1.10	4	5	19.625
450	18	457.0±4.10	17.6±1.20	4	5	23.211
500	20	508.0±4.50	19.5±1.30	4	5	28.577
550	22	558.8±5.00	21.5±1.40	4	5	34.656
600	24	609.6±5.40	23.4±1.50	4	5	41.151

* JIS standard

Application: Waste water drainage, low pressure/non-pressure application